



biothaneusa.com

Part Number	B07UT034BL520-BSEM-T034A
Width	0.730 (0.710 - 0.750)
Thickness	0.035 (0.030 - 0.040)
Webbing	Polyester
Coating / Hardness	PVC / 60A
Coating Texture	Sand Emboss
Gloss	Low Gloss
Min. Tensile Break Strength (lbf) <i>ASTM D6775</i>	450
90° Flex Test at Room Temperature (lbf)	0.62
Kinetic CoF - 1/2" Sled, Belt on Belt <i>ASTM D1894</i>	-
Hexbar Abrasion - % Strength Retention <i>ASTM D6770</i>	-
Taber Abrasion - grams lost <i>ASTM D4060</i>	0.245
Accelerated Weathering <i>ASTM G155</i>	Excellent
Vicat Softening Temp (°C) <i>ASTM D1525</i>	53.1
Glass Transition Temp (°C) <i>ASTM E1356</i>	-50.7
Clorox® Healthcare Bleach Immersion (3 days)	Excellent
Opti-Cide3® Immersion (3 days)	Good
Diversey Oxivir® 1 Immersion (3 days)	Fair
Diversey Virex® Tb Immersion (3 days)	Good
Biocompatibility - Cytotoxicity <i>ISO 10993</i>	Pass (2)
Biocompatibility - Irritation <i>ISO 10993</i>	Pass (0)
Resistance to Fungi <i>ASTM G21</i>	0 (no growth)

DISCLAIMER: Properties of BioThane® test results were compiled at BioThane Coated Webbing Corp. The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made to its accuracy, suitability for particular applications, or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Because of the variations in methods, conditions, and equipment used commercially in processing materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end-product performance are the responsibility of the user. SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE.